	OLTR	EMARE	Model LOW4-4021-2		
	LIQUID	SEPARATION	Extra Area - Extra Low Energy, Excellent	Productivity - Brackish Water El.	
Туре		Configuration:	Membrane Polymer:	Brine Spacer Material:	
		Spiral Wound	Composite Polyamide	Polypropylene	
Specifications		Permeate	Salt	Nominal Membrane	
		Flow:	Rejection:	Area:	
		1300 gpd	99,0% nominal	45ft <sup>2</sup>	
		(4,92 m³/d)	(98,0% minimum)	(4,2m <sup>2</sup> )	

Test Conditions (After 30 min of operation)	Solution NaCl	Applied Pressure:	Operating Temperature:	Permeate Recovery:	pH Range:
	500 ppm	100 psi <i>(6,9 bar)</i>	77 °F (25 °C)	10%	6,5 ÷ 7,0

## Dimensions

				_	
A	B	C	D <sub>F</sub>	D <sub>C</sub>	Weight
Total	ATD	Connection	Core Tube B	Extension	
Length	Diameter	Diameter	Feed Side	Conc. Side	
21.0 inches	3.95 inches	0.75 inches	1.2 inches	1.2 inches	4 lbs
(533,4 mm)	(100,3 mm)	<i>(19,1 mm)</i>	<i>(30,5 mm)</i>	(30,5 mm)	(1,8 Kg)
(F) ······D ·		A		<ul> <li>P Permeate</li> <li>F Feed</li> <li>Cn Concentration</li> </ul>	

Maximum Operating Limits							
Operating Pressure T Tape Wrapped	emperature	Pressure Drop	Feed Flow	Chlorine Concentratio	Feedwater on SDI (15min)	Feedwater Turbidity	
300 psi (20,7 bar)	113 °F <i>(4</i> 5 °C)	10 psi <i>(0,7 bar)</i>	12 gpm (45,4 lpm)	<0,1 ppm	5,0	1,0 NTU	
Other Operating Limits						ratio of concentrate to e flow for any element	
			3,0 ÷ 10,0	)	5:1		

The limitations shown in Operating Limits are for general use. The values may be more conservative for specific projects to ensure the best performance and longest life of the membrane.

Minimum permeate flow for individual elements 20 percent below listed flow. Elements are vacuum sealed in a polyethylene Notice: bag containing less than 1.0% sodium meta-bisulfite and 10% propylene glycol solution.

Guidelines: Permeate obtained from first hour of operation should be discarded.

Avoid static permeate-side backpressure at all times.

These membranes may be subject to drinking water application restrictions in some countries: please check the application status before use and sale.

For element loading use only glycerine to lubricate o-rings and brine seal.

The customer is fully responsible for the effects of incompatible chemicals on elements. The presence of free chlorine and other oxidizing agents will cause membrane failure, the damage is not covered under warranty. Oltremare believes the information and data contained herein to be accurate and useful. The information and data are offered in good

faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Oltremare assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Oltremare's products for the user's specific end uses.

No performance warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. Consult factory for detailed warranty information.

We reserve the right to modify or amend specifications without prior notice.